

# UNI-GROUP U.S.A.

## Tables – Permeable Interlocking Concrete Pavements

**TABLE 1**

**Grading Requirements for No. ASTM No. 8 Bedding Aggregate - ASTM D 448**

Sieve Size	Percent Passing
1/2 inch (12.5 mm)	100
3/8 inch (9.5 mm)	85 to 100
No. 4 (4.75 mm)	10 to 30
No. 8 (2.36 mm)	0 to 10
No. 16 (1.18 mm)	0 to 5

**TABLE 2**

**Grading Requirements for ASTM No. 57 Base – ASTM D 448**

Sieve Size	Percent Passing
1 1/2 inch (37.5 mm)	100
1 inch (25 mm)	95 to 100
1/2 inch (12.5 mm)	25 to 60
No. 4 (4.75 mm)	0 to 10
No. 8 (2.36 mm)	0 to 5

**TABLE 3**

**Grading Requirements for ASTM No. 2 Subbase – ASTM D 448**

Sieve Size	Percent Passing
3 inch (75 mm)	100
2 1/2 inch (63 mm)	90 to 100
2 inch (50 mm)	35 to 70
1 1/2 inch (37.5 mm)	0 to 15
3/4 inch (19 mm)	0 to 5

### CRUSHED STONE FILLER, BEDDING, BASE AND SUBBASE

- A. Crushed stone with 90% fractured faces, LA Abrasion < 40 per ASTM C 131, minimum CBR of 80% per ASTM D 1883.
- B. Do not use rounded river gravel.
- C. All stone materials shall be washed with less than 1% passing the No. 200 sieve.
- D. Joint/opening filler, bedding, base and subbase: conforming to ASTM D 448 gradation as shown in Tables 1, 2 and 3 below:

Note: No. 89, 9 or 10 gradations also may be used to fill narrow permeable paver joints.